


## Technical Data Sheet ARYAFILM - A420



ARYAFILM A420 is one side co-polymer coated Polyester film, this film is suitable for printing, metalizing, coating & improved bond strength in flexible packaging applications.



Sr. No.	Properties		Unit	Test Method	Target	Minimum	Maximum
			Gene	eral			•
4	Thickness		Micron	JBF Method	12	11.64	12.36
1			Gauge		48	46.56	49.44
2	Yield		M <sup>2</sup> /Kg	JBF Method	59.52	57.79	61.36
3	Density		gm/cc	ASTM D 1505	1.395		
4	Service Temp		°C	JBF Method	-70 to 150		
			Mecha	nical			
	Tensile Strength at break	MD/TD	Kg/cm <sup>2</sup>	ASTM D 882	2100	1900	2300
1			(Kpsi)		29.9	27.0	32.7
	Elongation at break	MD		130	90	170	
2		TD	<del>-</del> %	ASTM D 882	120	80	160
	Co-efficient of friction (One side to Other side)	Static		ASTM D 1894	0.50	0.40	0.60
3		Dynamic			0.45	0.35	0.55
			Ther	mal			L
4	Shrinkage @ 150 <sup>0</sup> C/30′	MD	- %	ASTM D 1204	1.8	1.2	2.4
1		TD			0.4	0.0	0.8
2	Melting Point		°C	DSC	252	250	255
	•		Opti	cal	I	I	ı
1	Haze		%	ASTM D 1003	3.5	2.5	4.5
2	Transmittance		%	ASTM D 1003	88	85	91
			Surface treat	tment level			
1	Co-Polymer coated side		Dynes/cm	ASTM D 2578	54	52	56
2	Plain Side		Dynes/cm	ASTM D 2578	44	42	46
			Barr	ier			
1	W.V.T.R. (38°C & 90% RH)		gm/m²/day	ASTM F 1249	40	30	50
			gm/100in²/day		2.58	1.94	3.23
2	O.T.R. (23°C & 0%RH)  ne Direction. TD = Transverse Direction		cc/m²/day	ASTM D 3985	100	80	120
			cc/100in <sup>2</sup> /day		6.45	5.16	7.74

MD = Machine Direction, TD = Transverse Direction

Storage & Handling: ARYA FILM need to be stocked in a closed warehouse & should not be exposed to direct sun light or light sources. Avoid extreme of humidity and heat. It is recommended to store below 40°C in dry places in original packing

Food Contact: ARYA FILM complies with EU10/2011 and US FDA regulations, Specific document and MSDS are available on request.

**Disclaimer:** The information given above is to the best of our knowledge and experience. Some of the properties can be changed as a result of suppliers' efforts to improve upon the quality or production efficiency of the subject. The information is believed to be true and accurate and is not intended to violate any statutory condition or right of a third party. JBF makes no warranty, express or implied, as to the fitness of the product for any specific use or purpose. The above data is purely for readers' consideration, investigation and verification and should be read in conjunction with the conditions for sale or contract

Website: www.jbfrak.com Email: filminfo@jbfrak.ae T.D.S No. Revision 05 JBF/TDS/649 10-July-2017