




Technical Data Sheet

ARYAFILM AZ431



ARYAFILM AZ431 is Metalized on Copolymer coated side with plasma treatment other side corona treated polyester film suitable for flexible packaging applications, especially for excellent gloss & barrier properties



- Metalized surface
- Copolymer Coated surface
- PET core Layer
- Corona treated surface

Sr. No.	Properties	Unit	Test Method	Target	Minimum	Maximum		
General								
1	Thickness	Micron	JBF Method	12.00	11.64	12.36		
		Gauge		48.00	46.56	49.44		
2	Yield	M ² /Kg	JBF Method	59.52	57.79	61.36		
Mechanical								
1	Tensile Strength at break	MD/TD	Kg/cm ² (Kpsi)	ASTM D 882	2100	1900	2300	
					29.9	27.0	32.7	
2	Elongation at break	MD	%	ASTM D 882	130	90	170	
		TD			120	80	160	
3	Co-efficient of friction One side to Other side	Static	--	ASTM D 1894	0.60	0.50	0.70	
		Dynamic			0.55	0.45	0.65	
4	Metal Bond Strength	gm/25 mm	TP-105-92	500	400	600		
Thermal								
1	Shrinkage @ 150 ^o C/30'	MD	%	ASTM D 1204	2.0	1.4	2.6	
		TD			0.4	0.0	0.8	
2	Melting Point	°C	DSC	252	250	255		
Surface treatment level								
1	Corona treated surface	Dynes/cm	ASTM D 2578	52	50	54		
Barrier								
Optical Density			M.V.T.R. (ASTM F 1249)			O.T.R. (ASTM D 3985)		
(JBF Method)			gm/m ² /day (38°C 90%RH)			cc/m ² /day (23°C 0 %RH)		
Target	Minimum	Maximu	Target	Minimum	Maximum	Target	Minimum	Maximum
2.2	2.0	2.4	0.9	0.7	1.1	1.0	0.8	1.2
2.5	2.3	2.7	0.7	0.5	0.9	0.8	0.6	1.0
2.8	2.6	3.0	0.5	0.3	0.7	0.6	0.4	0.8
3.0	2.8	3.2	0.3	0.1	0.5	0.4	0.2	0.6

MD = Machine Direction, TD = Transverse Direction

To convert from m²/day to 100 inch²/day divide the m² result by 15.5 ,

Storage & Handling: ARYA FILM need to be stocked in a closed warehouse & should not be exposed to direct sun light or light sources. Avoid extreme of humidity and heat. It is recommended to store below 40°C in dry places in original packing.

Food Contact: ARYA FILM complies with EC and FDA regulations on packaging for indirect contact with foodstuffs. Specific document and MSDS are available on request.

Disclaimer: The information given above is to the best of our knowledge and experience. Some of the properties can be changed as a result of suppliers' efforts to improve upon the quality or production efficiency of the subject. The information is believed to be true and accurate and is not intended to violate any statutory condition or right of a third party.

JBF makes no warranty, express or implied, as to the fitness of the product for any specific use or purpose. The above data is purely for readers' consideration, investigation and verification and should be read in conjunction with the conditions for sale or contract.

Website: www.jbfrak.com

Email: filminfo@jbfrak.ae

TDS No : JBF/TDS/M-458

Revision: 07

Date : 01-Jun-19